

## PTFE-COATED STANDARD

# CF203 BT

**CF203 BT** is a Versiv PTFE-coated fibreglass fabric with an etch coating on one side.

This product is typically used as a conveyor belt in extremely “sticky” or mildly abrasive environments such as foam manufacturing.

### TYPICAL PROPERTIES

| mil                           | METRIC       |                  | IMPERIAL     |                    | TEST METHOD    |
|-------------------------------|--------------|------------------|--------------|--------------------|----------------|
| <b>Standard Widths</b>        | 1000         | mm               | 39.4         | in                 | -              |
| <b>Weight</b>                 | 130          | g/m <sup>2</sup> | 3.8          | oz/yd <sup>2</sup> | FTMS 191A-5041 |
| <b>Thickness</b>              | 0.070        | mm               | 2.8          | mil                | FTMS 191A-5030 |
| <b>Tensile Strength</b>       | 120 x 90     | N/cm             | 70 x 50      | lb/in              | FTMS 191A-5102 |
| <b>Trap Tear Strength</b>     | 13 x 9       | N                | 2.9 x 2.0    | lb                 | FTMS 191A-5136 |
| <b>Temperature Resistance</b> | -150 to +260 | °C               | -240 to +500 | °F                 | -              |
| <b>PTFE Content</b>           | 63 %         |                  |              |                    | -              |

### FEATURES AND BENEFITS

- Thermally stable from -150 to +260 °C
- Chemically inert
- Non-stick and washable
- Dimensionally stable
- Non-flammable/fire resistant
- Low electrical losses
- Excellent heat transfer

### CONTACT US

+353 65 90 80 170

contact@versivcomposites.com

Versiv Composites Limited  
Kilrush, Co. Clare, V15 NW27, Ireland

www.versivcomposites.com

IMPORTANT: Pictures shown are for illustration purpose only. The values presented are typical values and should not be used for specification purposes. Contact your representative for more information. It is the user's responsibility to ensure the suitability and safety of Versiv Composites products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Versiv Composites Limited assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication, or application of the products into which the materials are incorporated by purchaser and/or user.

WARRANTY: We warranty specifications at delivery and honour claims for such breach of warranty for six (6) months after delivery. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential arising out of the use, misuse or inability to use this product(s). VERSIV COMPOSITES LIMITED DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Version 1 • Valid 11/2023 • Supersedes all previous versions

