

PTFE CAST FILMS

DF1100

DF1100 is a multilayer cast PTFE film with one surface modified to render it receptive to many conventional adhesives, elastomers, resins and potting compounds. The surface treatment was developed to assure that its application over pure PTFE would not degrade or discolor the basic film. After surface treatment, the PTFE film loses none of its excellent physical and electrical characteristics, expect that the surface treatment results in a natural color which does not affect any of the desired properties.

TYPICAL PROPERTIES

PROPERTY	METRIC	IMPERIAL	TEST METHOD
Maximum Width	1170 mm	46 in	-
Thickness Available	0.025 to 0.125 mm	1 to 5 mil	FTMS 191A-5030
Tensile Strength	29.6 MPa	4,300 psi	ASTM D-882
Elastic Modulus	413 MPa	60,000 psi	ASTM D-882
Coefficient of Friction	< 0.15		ASTM D-194
Elongation	400 %		ASTM D-882
Dielectric Strength	2000 volts/mil		ASTM D-257
Surface Arc Resistivity	Does not arc		ASTM D-495

FEATURES AND BENEFITS

- Isotropic properties
- Uniform tensile properties in machine and traverse direction
- Multilayer reducing the risk of pinholes or contamination
- Superior performance in a wide range of chemical, thermal, and electrical environments
- Colors and customization available on request

CONTACT US

☎ +353 65 90 80 170

✉ contact@versivcomposites.com

Versiv Composites Limited

Kilrush, Co. Clare, V15 NW27, Ireland

www.versivcomposites.com

IMPORTANT: Pictures shown are for illustration purpose only. The values presented are typical values and should not be used for specification purposes. Contact your representative for more information. It is the user's responsibility to ensure the suitability and safety of Versiv Composites products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Versiv Composites Limited assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication, or application of the products into which the materials are incorporated by purchaser and/or user.

WARRANTY: We warranty specifications at delivery and honour claims for such breach of warranty for six (6) months after delivery. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential arising out of the use, misuse or inability to use this product(s). VERSIV COMPOSITES LIMITED DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Version 2 • Valid 07/2026 • Supersedes all previous versions